

HARBORLITE® 700



PERLITE FILTER AID

IMERYS PERFORMANCE & FILTRATION MINERALS

Sales Office

154 rue de l'Université
75007 Paris – France
Tel: +33 1 49 55 63 00
Fax: +33 1 49 55 66 56

Production Site

Alzaia Trento 6
20094 CORSICO (MI) - Italy
Tel: +39 02 451 74200
Fax: +39 02 440 74224

PRODUCT

| | |
|---------------------|--------------|
| Production location | Milan, Italy |
| Product type | Perlite |

TYPICAL PHYSICAL PROPERTIES

| | |
|-------------------------|------------|
| Physical Form | Dry Powder |
| Colour | White |
| Permeability (darcy) | 2.6 |
| Cake Density (g/l) | 205 |
| Moisture (% as shipped) | 1 |
| Floaters (% by volume) | 44.8 |

TYPICAL CHEMICAL PROPERTIES (% by weight unless otherwise stated)

| | |
|--------------------------------|-----|
| SiO ₂ | 72 |
| Al ₂ O ₃ | 14 |
| Fe ₂ O ₃ | 0.7 |
| TiO ₂ | 0.1 |
| CaO | 0.3 |
| MgO | 0.1 |
| Na ₂ O | 4 |
| K ₂ O | 8.8 |

Typical values are not to be used as specifications

The physical or chemical properties of Harborlite® products represent typical, average values obtained in accordance with generally accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice.

Technical data shown above are considered accurate and reliable, however, no guarantee is given nor intended. For important Health & Safety information, please refer to MSDS.